

## Acrylic Polymer ACRYPET VH

PROPERTY	TEST METHOD	UNITS	VALUE
<b>THERMAL</b>			
Melt Flow Rate	ISO 1133 (230C,37.3N)	g/10min	2.0
Vicat Softening Point	ISO 306 (50N)	°C	107
Heat Deflection Temperature	ISO 75 (1.8 MPa)	°C	100
Specific Heat	JIS K7123	J/(g.°C)	1.5
Coefficient of Linear Expansion	ASTM D696	1/C	6 x 10 <sup>-5</sup>
Coefficient of Thermal Conductivity	ASTM C177	W/(mC)	0.2
Spiral Flow	MRC (2mm @ 230C)	mm	130
	MRC (2mm @ 250C)	mm	220
<b>OPTICAL</b>			
Total Light Transmission	ISO 13468 (3mm)	%	93
Haze	ISO 14782 (3mm)	%	0.3
Refractive Index	ASTM D542	-	1.49
<b>MECHANICAL</b>			
Tensile Strength	ISO 527 (1A/5)	MPa	77
Tensile Elongation	ISO 527 (1A/5)	%	6.0
Flexural Modulus	ISO 178	GPa	3.3
Flexural Strength	ISO 178	MPa	140
Charpy Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	1.4
	ISO 179/1eU	kJ/m <sup>2</sup>	20
<b>GENERAL</b>			
Specific Gravity	ISO 1183	g/cm <sup>3</sup>	1.19
Rockwell Hardness	ISO 2039-2	M Scale	101
Mould Shrinkage	MRC method	%	0.2 - 0.6
Water Absorption	ISO 62 ( 24hr)	%	0.30

The above data represents typical results obtained using standard test pieces, it should not form the basis of specifications. Information contained in this publication (and otherwise supplied to users) is based on our general experience and is given in good faith, but we are unable to guarantee its accuracy or to accept responsibility in respect of factors outside our knowledge or control. Freedom under patent, copyright and registered designs cannot be assumed.

Users of ACRYPET polymer should consult the relevant Material Safety Data Sheet.